

●Amber factice

Name	Acetone extract [%]	Free sulfur [%]	Ash [%]	Specific gravity at 20°C	Appearance	Net wt. [kgs]
Amber	17~23	≤0.1	≤1.5	1.04	Amber block	25
Amber L	27~33	≤0.1	≤1.5	1.01		
Amber#50	40~48	≤0.1	≤1.5	0.99		

○Applications

NR

SBR·NBR·EPDM etc.

○Uses

white or light colored and transparent products, rubber bands and other industrial articles

- Amber factice is a little softer than white factice, and is packed in plate form.
- It contains small quantity of magnesium oxide as stabilizer.
- "Amber L" and "Amber#50" contain naphthenic mineral oils.
- It causes the delay of vulcanizing same as white factice and the same actions are needed.