

●Golden factice

Name	Acetone extract [%]	Free sulfur [%]	Ash [%]	Specific gravity at 20°C	Appearance	Net wt. [kgs]
Golden	17~23	≤2.0	≤0.2	1.03	Yellow powder	15
Golden T	25~31	≤2.0	≤0.2	1.03		

○Applications

NR

SBR·NBR·CR·IIR·BR·CMS·EPDM etc.

○Uses

light colored or transparent rubbers, other industrial articles

- Golden factice is yellow-colored sulfur factice made by using hydrogenated rapeseed oil, and has good aging property.
- "Golden" is high grade type and its color is lighter than that of "GoldenT".
- Golden factice does not contain chlorine and it is not necessary to care about vulcanizing disturbance.
- Addition of 5 to 10 phr to IIR improves processability and gives bad influence little to rate of cure, aging resistance, and other properties.
- It can be used to modify the flow of oily paints, to adjust the tackiness of tackifiers, and to retain the viscosity of lubricant oils and cutting oils at high temperature.