

●Brown factice

Name	Acetone extract [%]	Free sulfur [%]	Ash [%]	Specific gravity at 20°C	Appearance	Net wt. [kgs]
Brown PR	14~20	≤1.5	≤0.2	1.05	Brown powder	20
Brown PR-S	33~39	≤1.5	≤0.2	1.02		
Brown A	17~23	≤1.5	≤0.2	1.05		
Brown AS	18~24	≤1.0	≤0.2	1.04		
Brown B	19~25	≤1.5	≤0.2	1.05		
Brown BS	20~26	≤1.0	≤0.2	1.04		
Brown#21	19~27	≤1.5	≤0.2	1.05		
Brown#30	39~45	≤1.5	≤0.2	1.04		

○Applications

NR

SBR·NBR·CR etc.

○Uses

printing rolls, OA rolls, autoparts, rubber sheets, rubber sponges, hoses, rubber-coated fabrics and other industrial articles

- Brown factice is sulfur factice made by using rapeseed oil and vegetable oil (recycled rapeseed oil mixed with some soybean oil).
- "Brown PR" and "Brown PRS" are made by using rapeseed oil only, and "Brown PRS" contains naphthenic mineral oil.
- "Brown A", "Brown AS", "Brown B", "Brown BS" and "Brown#30" are made by using mixture of rapeseed oil and vegetable oil, and "Brown#30" contains aromatic mineral oil.
- "Brown#21" is economical type made by using vegetable oil only.